

**IN THE SPECIFICATION:**

[0032] The filler applied as aqueous suspension on the fibre mesh can comprise between 0.5 g/m<sup>2</sup> and 50 g/m<sup>2</sup> of dry extract, preferably between 5 g/m<sup>2</sup> and 15 g/m<sup>2</sup> of dry extract.